

STATE OF NEBRASKA
DEPARTMENT OF ROADS
ADDENDUM NO. 3
AND
ELECTRONIC BIDDING SYSTEM
AMENDMENT NO. 1
PROJECT NO. EACNH-BH-30-7(115)
CONTROL NO. 21794
CALL ORDER F07
US-30, BLAIR TO KENNARD
LETTING DATE: MARCH 14, 2002

The Schedule of Items is amended as follows:

1. In Group 1, the bid item "1050 mm Driveway Culvert Pipe, Type 2, 3, 4 or 5" has been removed and the bid item "1050 mm Round Equivalent Drive Culvert Pipe, Type 2, 3, 4 or 5", with a quantity of 16.000 m, has been added.
2. In Group 10, the quantity for the bid item "Temporary Pavement Marking, Type Paint" is incorrect and should read 10,000.000 m.

The EBS generated bid items sheet must show these corrections or the bid will be considered void.

* * * * *

The Special Provisions are amended to include the following:

**47B CONCRETE PAVEMENTS AND
47BD CONCRETE FOR BRIDGES**

General

Section 1002 in the 1997 Standard Specifications and Supplemental Specifications is amended to include the following:

For the purpose of this Special Provision, Type IPN shall mean Type IP cement made with 15 to 25 percent natural pozzolan and Type IPF shall mean Type IP cement made with 15 to 25 percent Class F fly ash. All cements must conform to the requirements of Section 1004 in the 1997 Standard Specifications and Supplemental Specifications.

47BD Concrete for Bridges and Barriers

The 47BD concrete used in bridge decks, approach slabs, bridge rails, and barriers shall be proportioned using one of the alternates shown in Table I.

TABLE I (ENGLISH)
CLASS 47BD CONCRETE PROPORTIONS

Alt.	Cement Type	Pounds of Cement per Cu.Yd.	Pounds of Class F Fly Ash	Air Content Percent		Pounds of Total Agg. per Cu.Yd.		Ratio of Total Agg. Percent	Type of Coarse Agg.
				Min.	Max.	Min.	Max.		
1	I or II	590	130 Min.	5.0	7.5	2530	2950	30±3	Limestone
2	IPN	658	0*	5.0	7.5	2530	2950	30±3	Limestone
3	IPF	658	0**	5.0	7.5	2530	2950	30±3	Limestone
4	I or II	658***	0***	5.0	7.5	2530	2950	30±3	Limestone

TABLE I (METRIC)
CLASS 47BD CONCRETE PROPORTIONS

Alt.	Cement Type	Kg of Cement per Cu. Meter	Kg of Class F Fly Ash	Air Content Percent		Kg of Total Agg. per Cu.Meter		Ratio of Total Agg. Percent	Type of Coarse Agg.
				Min.	Max.	Min.	Max.		
1	I or II	350	77 Min.	5.0	7.5	1500	1750	30±3	Limestone
2	IPN	390	0*	5.0	7.5	1500	1750	30±3	Limestone
3	IPF	390	0**	5.0	7.5	1500	1750	30±3	Limestone
4	I or II	390***	0***	5.0	7.5	1500	1750	30±3	Limestone

* Class C or F fly ash may be substituted in the mix design provided the total pozzolan content does not exceed 25 percent. The mix may be modified by substituting an amount of fly ash equal to the weight of cement removed.

** No additional fly ash substitution is allowed.

*** Total alkali content shall not exceed 3 lbs./yd.³ (1.8 Kg/m³)

Water reducing and set retarding admixtures shall be used in accordance with the manufacturer's recommendations of dosage rates.

47B Concrete Pavements

The 47B concrete used in concrete pavements shall be proportioned using one of the alternates shown in Table II.

TABLE II (ENGLISH)
CLASS 47B CONCRETE PAVEMENT PROPORTIONS

Alt.	Cement Type	Pounds of Cement per Cu.Yd.	Pounds of Class F Fly Ash	Air Content Percent		Pounds of Total Agg. per Cu.Yd.		Ratio of Total Agg. Percent	Type of Coarse Agg.
				Min.	Max.	Min.	Max.		
1	I or II	510	110 Min.	5.0	7.5	2876	3130	30±3	Limestone
2	IPN	564*	0*	5.0	7.5	2876	3130	30±3	Limestone
3	IPF	564**	0**	5.0	7.5	2876	3130	30±3	Limestone
4	I or II	564***	0***	5.0	7.5	2876	3130	30±3	Limestone

TABLE II (METRIC)
CLASS 47B CONCRETE PAVEMENT PROPORTIONS

Alt.	Cement Type	Kg of Cement per Cu. Meter	Kg of Class F Fly Ash	Air Content Percent		Kg of Total Agg. per Cu.Meter		Ratio of Total Agg. Percent	Type of Coarse Agg.
				Min.	Max.	Min.	Max.		
1	I or II	303	65 Min.	5.0	7.5	1706	1857	30±3	Limestone
2	IPN	335*	0*	5.0	7.5	1706	1857	30±3	Limestone
3	IPF	335**	0**	5.0	7.5	1706	1857	30±3	Limestone
4	I or II	335***	0***	5.0	7.5	1706	1857	30±3	Limestone

* Class C or F fly ash may be substituted in the mix design provided the total pozzolan content does not exceed 25 percent. The mix may be modified by substituting an amount of fly ash equal to the weight of cement removed.

** No additional fly ash substitution is allowed.

*** Total alkali content shall not exceed 3 lbs./yd.³ (1.8 Kg/m³)

Water reducing admixtures shall be used in accordance with the manufacturer's recommendations of dosage rates.

* * * * *

Upon execution of the contract, the plans will be revised to reflect these changes.

DEPARTMENT OF ROADS

Claude Oie
Construction Engineer

Issued: March 12, 2002

CO:F07AD303

NOTICE: Only the contractors issued bidding proposals receive this addendum and responsibility for notifying any potential subcontractors or suppliers remains with the contractor.