

SECTION 1013 -- BITUMINOUS LIQUID COMPOUNDS FOR CURING CONCRETE

1013.01 -- Description

The compound shall consist essentially of an asphaltic base and shall be of a consistency suitable for spraying at temperatures existing at the time of construction operations. It shall form a continuous, uniform film. It shall be free of precipitated matter caused by conditions of storage or temperature. The compound shall be relatively nontoxic.

1013.02 -- Material Characteristics

When tested in accordance with AASHTO T 155, the loss of water shall not be more than 0.55 kg/m² of surface area at 3 days, unless otherwise specified by the Engineer.

1013.03 -- Acceptance Requirements

Bituminous liquid curing compounds approved for use are shown on the NDR Approved Products List.